



KAOLİN
ENDÜSTRİYEL MINERALLER SAN.VE TİC.A.Ş.

Yenişehir Mah. Turgut Özal Blv.
No:36, Darende İş Mrk. D:12
Ataşehir - İstanbul / TURKEY
Tel: +90 216 455 23 12
Fax: +90 216 455 24 93
info@kaolin.com.tr

SPECIFICATION

BENTONITE – B5045

1. CHEMICAL ANALYSIS, Typical, %

SiO ₂	71.55
Al ₂ O ₃	14.10
Fe ₂ O ₃	0.90
TiO ₂	0.10
CaO	1.30
MgO	2.00
Na ₂ O	0.70
K ₂ O	1.10
L.O.I.	4.85

2. PARTICLE SIZE, %

+45 microns 7.50 ± 2.50

3. MOISTURE, %

12.0 max